

## HG 232 EVA, HOT MELT ADHESIVE FOR CASE AND CARTON SEALING

### TYPICAL APPLICATIONS

- For lower temperature applications, required for the more demanding application
- Suitable for all hot melt glue equipment used with secondary packaging applications

### PRODUCT FEATURES

- Aggressive hot tack
- Excellent adhesion
- Excellent machining properties
- Exhibits fast set speeds

### CONSTRUCTION

#### STANDARD WIDTH

NA  
NA

#### STANDARD LENGTH

NA  
NA

#### STANDARD CORE SIZE

NA

### APPLICABLE STANDARDS

ASTM D 3236

### STORAGE & USAGE CONDITIONS

For best results, use product within 365 days.

When handling and working with hot melt adhesives, always wear protective clothing and eye protection. To minimize the risk of flammable vapors, do not exceed 400 F melt temperature.

For best results, allow product to cool and manually remove excess adhesive with scraper. Consult your hot melt equipment manufacturer for proper clean-up procedures.

Under normal conditions of use, this product is considered nontoxic. Consult the SDS for additional information.

### COLOR



### PHYSICAL PROPERTIES

|                               | STANDARD                  | METRIC                    |
|-------------------------------|---------------------------|---------------------------|
| Application Temperature Range | 250 F to 300 F            | 121 C to 148 C            |
| Softening Point               | 162 F (+/- 2.0)           | 72 C (+/- 2.0)            |
| Viscosity                     | 900 cps (+/- 180) @ 275 F | 900 cps (+/- 180) @ 176 C |

Physical and performance characteristics are obtained tests recommended by ASTM, government agencies or Shurtape Technologies, LLC, Quality Assurance and Technical Service departments and do not represent a guarantee of product performance. Individual cases may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

