

PE 444 UV-RESISTANT STUCCO MASKING TAPE

TYPICAL APPLICATIONS

- For masking surfaces, such as windows and doors, during stucco application and painting
- Used to reinforce boat heat shrink wrap seams to create a tight, continuous seal that protects the vessel from the elements during seasonal storage or transportation.
- Used in construction applications for temporarily securing poly sheeting and temporary containment barriers, as well as surface protection

PRODUCT FEATURES

- UV-resistant backing helps maintain performance during extended outdoor exposure
- Excellent conformability
- Maintains a watertight seal
- Removes cleanly
- Meets flame-retardant requirements of NFPA 701 and ASTM E84 Class A (Class I) for applications requiring compliance with building and construction fire performance standards

CONSTRUCTION

Backing: Polyethylene film

Adhesive: Synthetic rubber adhesive

STANDARD WIDTH

1.88 in

48 mm

STANDARD LENGTH

60.1 yd

55 m

Lead times may apply. Please contact Shurtape customer service for information related to stock and non-stock sizes and colors.

STANDARD CORE SIZE

3 in

APPLICABLE STANDARDS

ASTM E84 Class A (Class I) Rating

NFPA 701

STORAGE & USAGE CONDITIONS

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 12 months of date of shipment.

Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminants.

COLOR



PHYSICAL PROPERTIES

	STANDARD	METRIC
Adhesion to Stainless Steel	80 oz/in width	8.76 N/10 mm
Elongation	76%	76%
Service Temperature Range	32 F to 160 F	0 C to 71 C
Tensile	19 lbs/in width	33.3 N/10 mm
Thickness	7.0 mils	0.18 mm
Water Vapor Transmission Rate	1.7 g/m ² /24 h	1.7 g/m ² /24 h

Physical and performance characteristics shown above are obtained from tests recommended by PSTC, ASTM, government agencies or Shurtape Technologies, LLC, Quality Assurance and Technical Service departments and do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

